

# RTP 199 X 70815

Polypropylene  
RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'  
The data for this material has not been recently verified.  
Please contact RTP Company for current information prior to specifying this grade.

General Information			
Filler / Reinforcement	Long glass fiber, 30% filler by weight		
Features	Chemical coupling		
RoHS Compliance	Contact manufacturer		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage - Flow (4.00 mm)	0.10 - 0.30	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7300	MPa	ISO 527-2
Tensile Stress (Yield)	120	MPa	ISO 527-2
Tensile Strain (Break)	2.0 - 3.0	%	ISO 527-2
Flexural Modulus	6900	MPa	ISO 178
Flexural Stress	170	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact <sup>1</sup>	21	kJ/m <sup>2</sup>	ISO 180/1A
Unnotched Izod Impact Strength <sup>2</sup>	60	kJ/m <sup>2</sup>	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	153	°C	ISO 75-2/A
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	190 - 230	°C	
Mold Temperature	30.0 - 65.0	°C	
Injection Pressure	70.0 - 105	MPa	
Injection instructions			
Use a reverse barrel profile. To maximize fiber length, the following injection barrel, screw, and tip designs should be followed. L/D ratio 16/1 - 22/1, Compression ratio 2:1, Flight depth 5 mm minimum, in feed section, Screw diameter 16.5 - 20 mm minimum, Compression section length 12 - 13 diameters, Check ring valve assembly - free flow type no restrictions, Nozzle orifice 6 mm diameter. Feed throat from hopper to machine must have sufficient opening to prevent bridging of long pellet composition.			
NOTE			
1.	4 mm thickness		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

