

Sanren Q400 (On-spec.)

Low Density Polyethylene
SINOPEC Shanghai Petrochemical Co. Ltd.

Message:

The oblate pellet product is colourless with excellent chemical stability. Under normal conditions, the product is acid resistant, alkali resistant and salt resistant. It possesses certain mechanical properties and water-proof characteristics and air permeability.
Scope of Application: Light-duty film, and mulching film.

General Information			
Features	Low density		
	Homopolymer		
	alkali resistance		
	acid resistance		
Uses	Films		
Appearance	Colorless		
Forms	Particle		
Processing Method	Blow molding		
Physical	Nominal Value	Unit	Test Method
Density	0.922	g/cm ³	Internal method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.2 - 4.8	g/10 min	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	> 9.00	MPa	Internal method
Tensile Elongation (Break)	> 450	%	Internal method
Optical	Nominal Value	Unit	Test Method
Haze	< 11	%	Internal method
Additional Information	Nominal Value	Unit	
Fish Eye			
0.300 to 2.00mm		pcs/1200 cm ²	
Linking: 0.500 to 2.00mm		pcs/20 cm ²	
Hue			
Impurities (> 100.0 μm)		pcs/100 g	
Streaks	B		
Cleanliness: <20 pieces/kg			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

