

ADDINYL B2H G15

Polyamide 6

ADDIPLAST

Message:

ADDINYL B2H G15 is a Polyamide 6 (Nylon 6) material filled with 15% glass bead. It is available in Africa & Middle East, Asia Pacific, Europe, or Latin America.

Important attributes of ADDINYL B2H G15 are:

Flame Rated

Flame Retardant

Typical applications include:

Automotive

Electrical/Electronic Applications

Wire & Cable

General Information				
Filler / Reinforcement		Glass Bead, 15% Filler by Weight		
Additive		Flame Retardant		
Features		Flame Retardant		
		Halogenated		
Uses		Automotive Applications		
		Electrical/Electronic Applications		
		Telecommunications		
Forms		Pellets		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.47	--	g/cm ³	ISO 1183/A
Hardness	Dry	Conditioned	Unit	Test Method
Shore Hardness (Shore D)	88	86		ISO 868
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Stress (Break)	62.0	32.0	MPa	ISO 527-2
Tensile Strain (Break)	4.0	25	%	ISO 527-2
Flexural Modulus	3600	1600	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	2.0	3.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	25	65	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength	3.5	3.0	kJ/m ²	ISO 180/1A
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	98.0	--	°C	ISO 75-2/Af

Melting Temperature (DSC)	220	--	°C	ISO 3146
Electrical	Dry	Conditioned	Unit	Test Method
Comparative Tracking Index (Solution A)	250	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.60 mm)	V-0	--		UL 94
Glow Wire Ignition Temperature	960	--	°C	IEC 60695-2-13
Oxygen Index	30	--	%	ISO 4589-2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

