

Hifax TYC 258P G14008

Polypropylene Copolymer
LyondellBasell Industries

Message:

Hifax TYC 258P G14008 is a 30% talc reinforced, impact modified and UV stabilized polypropylene copolymer for injection moulding. It combines an excellent flowability with a low coefficient of linear thermal expansion and very good processability. The grade has been specifically designed for moulding of large complex parts that require good dimensional stability.

General Information			
Filler / Reinforcement	Talc,30% Filler by Weight		
Features	Good Dimensional Stability		
	Good Processability		
	Good UV Resistance		
	High Flow		
	Impact Modified		
	Low CLTE		
	Low Shrinkage		
Uses	Automotive Exterior Parts		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	21	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	18.0	MPa	ISO 527-2/50
Tensile Strain (Break, 23°C)	50	%	ISO 527-2/50
Flexural Modulus ¹ (23°C)	1800	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-30°C	3.3	kJ/m ²	
23°C	30	kJ/m ²	
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

