

NEFTEKHIM PE 6753G (526H7)

High Density Polyethylene
Nizhnekamskneftekhim Inc.

Message:
Product obtained by gas phase polymerization of ethylene in presence of complex metalorganic catalysts.
Stabilization recipe: antacid, antioxidant, thermostabilizer, processing aid, dispersing agent, carbon black
Application: carbon black filled compound for non-pressure pipes.
Technical requirements: TU 2211-145-05766801-2008

| General Information | | | |
|--|---------------------|-------------------|-------------|
| Additive | Acid Neutralizer | | |
| | Antioxidant | | |
| | Carbon Black | | |
| | Heat Stabilizer | | |
| | Processing Aid | | |
| Features | Acid Resistant | | |
| | Antioxidant | | |
| | Dispersible | | |
| | Good Processability | | |
| | Heat Stabilized | | |
| Uses | Piping | | |
| Forms | Pellets | | |
| Processing Method | Pipe Extrusion | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 0.950 to 0.954 | g/cm ³ | ASTM D1505 |
| Melt Mass-Flow Rate (MFR) (190°C/5.0 kg) | 0.60 to 0.80 | g/10 min | ASTM D1238 |
| Melt Flow Ratio - MFR 21.6 kg/MFR 5.0 kg | > 70.0 | | ASTM D1238 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT