

EVICOM™ GA1/081

Flexible Polyvinyl Chloride

INEOS Compounds

Message:

Lead-free version of GA1/733

| General Information | | | |
|--------------------------------------|----------------------------|-------------------|--------------|
| Features | Good Flexibility | | |
| | Low (to None) Lead Content | | |
| Appearance | Opaque | | |
| Forms | Pellets | | |
| Processing Method | Profile Extrusion | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.40 | g/cm ³ | BS 2782 620A |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A, 15 sec) | 95 | | BS 2782 365B |
| BS Softness | 11 | | BS 2782 365A |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | 19.0 | MPa | BS 2782 320A |
| Tensile Elongation (Break) | 240 | % | BS 2782 320A |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT