OnFlex™ S EH 70A-3S7004

Thermoplastic Elastomer

PolyOne Corporation

Message:

OnFlex $^{\text{M}}$ -S EH thermoplastic elastomer polymer is mixed with hydrogenated styrene block copolymer. In addition to having OnFlex $^{\text{M}}$ The main characteristics of-S products, such as high hardness, good mechanical properties, good processability, good coloring properties, and a large operating temperature range, this series of polymers has excellent cost performance. OnFlex $^{\text{M}}$ -S EH polymer is filled with other substances, so it is opaque and has a relatively high density.

General Information					
Features	General				
Uses	Electrical appliances				
	Industrial application				
	Application in Automobile Field				
	General				
	Consumer goods application field				
RoHS Compliance	RoHS compliance	RoHS compliance			
Forms	Particle	Particle			
Processing Method	Injection molding				
Physical	Nominal Value	Unit	Test Method		
Density	1.20	g/cm³	ISO 1183		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore A)	70		ISO 868		
Elastomers	Nominal Value	Unit	Test Method		
Tensile Stress			ISO 37		
100% strain	2.40	MPa	ISO 37		
300% strain	3.20	MPa	ISO 37		
Tensile Stress (Break)	5.00	MPa	ISO 37		
Tensile Elongation (Break)	550	%	ISO 37		
Tear Strength	26	kN/m	ISO 34-1		
Compression Set			ISO 815		
23°C, 72 hr	29	%	ISO 815		
70°C, 22 hr	50	%	ISO 815		
100°C, 22 hr	78	%	ISO 815		
Flammability	Nominal Value	Unit	Test Method		
Fogging (100°C)	1.2	mg	DIN 75201B		
Odor rating	2.40		VDA 270		
General Material Type	Styrene thermoplastic elast	Styrene thermoplastic elastomers (TES)			
	Nominal Value		Test Method		

Injection	Nominal Value	Unit	
Processing (Melt) Temp	180 - 220	°C	
Mold Temperature	30.0 - 60.0	°C	
Injection Rate	Fast		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

