ELASTOSIL® E 60

Silicone

Wacker Chemie AG

Message:

Silicone Rubber, RTV-1
Baking Molds, Household Appliances
Baking Tray Coating, Food Processing
Baking Tray Coating, Paints & Coatings

General Information			
Features	Food Contact Acceptable		
Uses	Coating Applications		
Uncured Properties	Nominal Value	Unit	Test Method
Color	Red		
Density			
	1.12	g/cm³	DIN 53217
	1.13	g/cm³	ISO 1183
Viscosity	70	Pa·s	Brookfield
Curing Time	12	hr	
Skin Forming Time ¹ (23°C)	15.0 to 20.0	min	
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	35		DIN 53505
Tensile Strength	2.80	MPa	DIN 53504
Tensile Elongation at Break	280	%	DIN 53504
NOTE			
1.	50% R.H		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

