

TECHNYL® C 218 V40 BLACK 21

Polyamide 6
Solvay Engineering Plastics

Message:
TECHNYL C 218 V40 is a polyamide 6 with 40% of glass fiber and with thermal stability.

General Information				
Filler / Reinforcement		Glass Fiber,40% Filler by Weight		
Features		Good Dimensional Stability		
		Good Impact Resistance		
		Good Thermal Stability		
Appearance		Black		
		Natural Color		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.45	--	g/cm ³	ASTM D792
Water Absorption (Equilibrium, 23°C, 50% RH)	0.90	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	13100	7300	MPa	ISO 527-2
Tensile Stress (23°C)	210	140	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.3	3.5	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	18	34	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	110	120	kJ/m ²	ISO 179
Notched Izod Impact Strength (23°C)	16	34	kJ/m ²	ISO 180
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	214	--	°C	ISO 75-2/A
Peak Melting Temperature	222	--	°C	ASTM D3418
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (23°C)	1.0E+15	1.0E+11	ohms · cm	IEC 60093
Electric Strength (23°C)	--	22	kV/mm	IEC 60243-1
Relative Permittivity (23°C, 1 MHz)	3.80	4.50		IEC 60250
Dissipation Factor (23°C, 1 MHz)	0.020	9.0E-3		IEC 60250

Comparative Tracking Index	550	475	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating	HB	--		UL 94
Glow Wire Flammability Index (1.60 mm)	650	--	°C	IEC 60695-2-12
Oxygen Index	23	--	%	ISO 4589-2
Injection	Dry	Unit		
Rear Temperature	240 to 260		°C	
Middle Temperature	230 to 240		°C	
Front Temperature	240 to 250		°C	
Nozzle Temperature	230 to 240		°C	
Mold Temperature	80.0 to 100		°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT