Elvax® 240A

Ethylene Vinyl Acetate Copolymer

DuPont Packaging & Industrial Polymers

Message:

DuPont™ Elvax® 240A is an ethylene-vinyl acetate copolymer resin for use in industrial applications.

Composition

28 % By Weight Vinyl Acetate comonomer content

Thermal Stabilizer: BHT antioxidant

Applications

Elvax® resins can be used in a variety of applications involving molding, compounding, extrusion, adhesives, sealants, and wax blends. For additional information and properties associated with specific applications, please refer to the Grade Selector Guides found on the Elvax® website for industial applications. http://www.dupont.com/industrial-polymers/elvax/index.html.

General Information	
Additive	Antioxidant
	Heat Stabilizer
Features	Antioxidant
	Copolymer
	Food Contact Acceptable
	Heat Stabilized
Uses	Adhesives
	Blending
	Compounding
	Industrial Applications
	Sealants
	Wire Jacketing
Agency Ratings	FDA 21 CFR 177.1350(a)(1)
Forms	Pellets
Processing Method	Blow Molding
	Compounding
	Compression Molding
	Extrusion
	Injection Molding
	Sheet Extrusion
	Structural Foam Molding

Physical	Nominal Value	Unit	Test Method		
Specific Gravity	0.951	g/cm³	ASTM D792, ISO 1183		
Melt Mass-Flow Rate (MFR) (190°C/2.16					
kg)	43	g/10 min	ASTM D1238, ISO 1133		

Vinyl Acetate Content	28.0	wt%	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	40.0	°C	ASTM D1525, ISO 306
Melting Temperature (DSC)	74.0	°C	ASTM D3418, ISO 3146
Additional Information	Nominal Value	Unit	
Processing Temperature	< 230	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

