

PREMIER™ A230-HTHF

Polycarbonate + ABS

Chomerics, div. of Parker Hannifin Corp.

Message:

PREMIER™ is the world's first and most versatile commercially available conductive thermoplastic for real world EMI shielding solutions. It is a blend of PC/ABS thermoplastic polymer alloys and conductive fillers engineered for stable electrical, mechanical, and physical performance. The conductive filler technology utilizes nickel plated carbon (Ni-C) fibers as the base filler. In the case of higher shielding versions, Nickel-Graphite (Ni-C) powder is blended with the fiber base to deliver enhanced performance.

| General Information | | | |
|----------------------------|------------------------------------|-------------------|-------------|
| Filler / Reinforcement | Nickel-Coated Carbon Fiber | | |
| Features | Electrically Conductive | | |
| | Electromagnetic Shielding (EMI) | | |
| | Good Corrosion Resistance | | |
| | Halogen Free | | |
| | High Tensile Strength | | |
| | Low Density | | |
| | Non-Corrosive | | |
| | Recyclable Material | | |
| Uses | Automotive Applications | | |
| | Consumer Applications | | |
| | Electrical/Electronic Applications | | |
| | Industrial Applications | | |
| | Military Applications | | |
| | Telecommunications | | |
| Agency Ratings | EU Unspecified Rating | | |
| RoHS Compliance | RoHS Compliant | | |
| Forms | Pellets | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.39 | g/cm ³ | ASTM D3763 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus | 6700 | MPa | ASTM D638 |
| Tensile Strength (Break) | 71.0 | MPa | ASTM D638 |
| Tensile Elongation (Break) | 1.2 | % | ASTM D638 |
| Flexural Modulus | 6300 | MPa | ASTM D790 |
| Flexural Strength | 100 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact | 53 | J/m | ASTM D412 |

| Unnotched Izod Impact | 180 | J/m | ASTM D412 |
|---|---------------|----------|-------------|
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1.8 MPa, Unannealed) | 120 | °C | ASTM D648 |
| CLTE - Flow | 3.0E-5 | cm/cm/°C | ASTM D696 |
| Thermal Conductivity | 0.59 | W/m/K | ASTM D5470 |
| RTI Elec | 85.0 | °C | UL 746 |
| RTI Imp | 85.0 | °C | UL 746 |
| RTI Str | 85.0 | °C | UL 746 |
| Electrical | Nominal Value | Unit | |
| Surface Resistivity | 0.60 | ohms | |
| Volume Resistivity | 0.060 | ohms·cm | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

