

THERMOLAST® K TC0GPZ (Series: GP/FG)

Thermoplastic Elastomer

KRAIBURG TPE

Message:

The GP/FG Series is your material solution for a variety of different applications. It is particularly appropriate for passenger compartments. The compounds are available in natural and black colors.

Typical applications

Car mats

Function and design elements

Handles (tools, toolboxes, skipoles)

Seals

Soft touch surface (thumb wheels, push buttons, switches)

Material advantages

Adhesion to PP

Easy coloring (compounds in natural colors)

Excellent mechanical properties

Excellent processing behavior

Fulfills specifications for automotive interior

Pleasant surface feel (Soft touch)

UL 94 HB listed

| General Information | | | |
|---|------------------------|-------------------|-------------|
| UL YellowCard | E353857-101117931 | E214822-586887 | |
| Features | Workability, good | | |
| | Good adhesion | | |
| Uses | Handle | | |
| | Seals | | |
| | Car interior parts | | |
| | Soft touch application | | |
| Appearance | Black | | |
| Processing Method | Extrusion | | |
| | Injection molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 1.10 | g/cm ³ | ISO 1183 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore D) | 33 | | ISO 7619 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Stress ¹ (Yield) | 14.5 | MPa | ISO 37 |
| Tensile Elongation ² (Break) | 650 | % | ISO 37 |
| Tear Strength ³ | 45 | kN/m | ISO 34-1 |
| Compression Set ⁴ | | | ISO 815 |
| 23°C, 72 hr | 41 | % | ISO 815 |

| | | | |
|-----------------------|----------------------|-------------|--------------------|
| 70°C, 24 hr | 60 | % | ISO 815 |
| 100°C, 24 hr | 70 | % | ISO 815 |
| Flammability | Nominal Value | | Test Method |
| Flame Rating | HB | | UL 94 |
| Extrusion | Nominal Value | Unit | |
| Drying Temperature | 60.0 - 80.0 | °C | |
| Drying Time | 2.0 - 4.0 | hr | |
| Cylinder Zone 1 Temp. | 160 | °C | |
| Cylinder Zone 2 Temp. | 180 | °C | |
| Cylinder Zone 3 Temp. | 200 | °C | |
| Die Temperature | 200 - 230 | °C | |

NOTE

- | | |
|----|--------------------------------------|
| 1. | Type S2, 200 mm/min |
| 2. | Type S2, 200 mm/min |
| 3. | Method B, right-angle specimen (cut) |
| 4. | Method A |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

