

MBA PP 2182

Polypropylene Copolymer

MBA Polymers

Message:

A post-consumer recycled polypropylene copolymer with a very high melt flow rate for injection moulding applications. Available in standard black (reference 90/04).

General Information	
Recycled Content	Yes
Features	Copolymer
	High liquidity
Appearance	Black
Forms	Particle
Processing Method	Extrusion
	Injection molding

Physical	Nominal Value	Unit	Test Method
Density	0.930	g/cm ³	Internal method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	35	g/10 min	ISO 1133

Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break, 23°C)	16.5	MPa	ISO 527-2/50
Flexural Modulus (23°C)	850	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	6.5	kJ/m ²	ISO 180/1A

Injection	Nominal Value	Unit
Drying Temperature	80.0	°C
Drying Time	1.0 - 2.0	hr
Suggested Max Moisture	0.050 - 0.10	%
Processing (Melt) Temp	190 - 220	°C
Mold Temperature	30.0 - 60.0	°C

Extrusion	Nominal Value	Unit
Drying Temperature	80.0	°C
Drying Time	1.0 - 2.0	hr
Suggested Max Moisture	0.050 - 0.10	%
Melt Temperature	180 - 210	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

