

Shin-Etsu Elastomer SV-15000U

Silicone Rubber, HTV

Shin-Etsu Silicones of America

Message:

SV-15000U is one of a series of easy processing, no post cure silicone rubber bases. It can be used in a variety of applications requiring finishing by molding, extruding or calendering.

This product can be blended with other Shin-Etsu general purpose or no post cure bases for intermediate properties. The choice between these bases will depend on specific requirements. This product can also be extended with filler.

Typical Applications

Roll covers.

Diaphragms.

General Information		
Features	Workability, good	
	General	
Uses	Diaphragm	
	General	
Processing Method	Extrusion	
	Calendering	
	Injection molding	
Physical	Nominal Value	Unit
Specific Gravity	1.13	g/cm ³
Hardness	Nominal Value	Unit
Durometer Hardness	51	
Elastomers	Nominal Value	Unit
Tensile Stress (100% Strain)	1.39	MPa
Tensile Strength	9.16	MPa
Tensile Elongation (Break)	440	%
Tear Strength ¹	15.4	kN/m
Compression Set (177°C, 22 hr)	9.0	%
Thermoset	Nominal Value	Unit
Post Cure Time (200°C)	4.0	hr
Additional Information	Nominal Value	Unit
Cure Agent	DBPH	
Press / Post Cure: Press		
Uncured Properties	Nominal Value	Unit
Curing Time	0.17	hr
NOTE		
1.	B mould	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

