

LNP™ THERMOCOMP™ RB00A compound

Polyamide 66

SABIC Innovative Plastics Europe

Message:

50% glass beads filled Polyamide 66 injection moulding resin.

Also known as: LNP* THERMOCOMP* Compound RB10010

Product reorder name: RB00A

General Information			
Filler / Reinforcement	Glass Bead,50% Filler by Weight		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.56	g/cm ³	ISO 1183
Molding Shrinkage - Flow ¹	0.50 to 0.80	%	Internal Method
Water Absorption (Saturation, 23°C)	4.5	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6200	MPa	ISO 527-2/1
Tensile Stress (Break)	85.0	MPa	ISO 527-2/5
Tensile Strain (Break)	2.5	%	ISO 527-2/5
Flexural Modulus ²	6000	MPa	ISO 178
Flexural Stress	140	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength ³ (23°C)	30	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength ⁴			ISO 180/1A
-40°C	3.0	kJ/m ²	
-20°C	4.0	kJ/m ²	
23°C	5.0	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁵			
0.45 MPa, Unannealed, 100 mm Span	245	°C	ISO 75-2/Be
1.8 MPa, Unannealed, 100 mm Span	175	°C	ISO 75-2/Ae
Vicat Softening Temperature	255	°C	ISO 306/A50
CLTE			ISO 11359-2
Flow : 23 to 60°C	3.0E-5	cm/cm/°C	
Transverse : 23 to 60°C	3.0E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index			IEC 60112
--	500	V	
Solution B	400	V	

Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm, Testing by SABIC)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	75.0 to 85.0	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	0.20	%	
Hopper Temperature	60.0 to 80.0	°C	
Rear Temperature	270 to 290	°C	
Middle Temperature	260 to 280	°C	
Front Temperature	260 to 280	°C	
Nozzle Temperature	250 to 270	°C	
Processing (Melt) Temp	260 to 290	°C	
Mold Temperature	70.0 to 120	°C	
NOTE			
1.	Tensile Bar		
2.	2.0 mm/min		
3.	80*10*4 sp=62mm		
4.	80*10*4		
5.	120*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT