

ExxonMobil™ HDPE HMA 016

High Density Polyethylene Resin
ExxonMobil Chemical

Message:

HMA 016 is a high density polyethylene grade, which is characterized by fast recycling and good impact strength. It has high gloss and high shape stability.

General Information			
Additive	heat stabilizer		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	20	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (50°C, 10% Igepal)	2.00	hr	ASTM D1693
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	23.0	MPa	ISO 527-2/1A/50
Tensile Strain			ISO 527-2/1A/50
Yield	10	%	ISO 527-2/1A/50
Fracture	> 100	%	ISO 527-2/1A/50
Flexural Modulus	970	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	4.0	kJ/m²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	64.0	°C	ISO 75-2/B
Peak Melting Temperature	133	°C	ASTM D3418
Additional Information			
成型性能是使用基于 ISO 294-1 标准的 4 mm(157.5 mil)厚注塑成型试样测定的.1. 0.45 MPa,70 psi 2.ESCR 是基于 2 mm(78.7 mil)厚的模压板(F50,10 % Igepal,50°C,122°F)所测定			
Legal statement			

有关潜在食品接触应用合规信息(例如:FDA,EU,HPFB),请与埃克森美孚化工客户服务代表联系.本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT