THERMOLAST® K TC7LEZ (Series: UV/FG)

Thermoplastic Elastomer

KRAIBURG TPE

Message:

The UV/FG Series is your material solution for applications requiring high UV resistance. It is particularly appropriate for automotive exterior and interior components.

Typical applications

Cowls gaskets

Roof rims

Soft touch for grips, switches and mats

Water deflectors

Window encapsulations

Material advantages

Easy flowing

Excellent mechanical properties

Fulfills specifications for automotive interior

Perfect adhesion to PP

Perfect surface finish

Tested according PV3930 for outdoor use

General Information					
Features	Good Adhesion				
	Good Flow				
	Good UV Resistance				
	Outstanding Surface Finish				
Uses	Automotive Exterior Parts				
	Automotive Interior Parts				
	Gaskets				
	Soft Touch Applications				
	Switches				
Appearance	Black				
Processing Method	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Density	0.980	g/cm³	ISO 1183		
Spiral Flow ¹	67.0	cm			
Hardness	Nominal Value	Unit	Test Method		
Shore Hardness (Shore A)	70		ISO 7619		
Elastomers	Nominal Value	Unit	Test Method		
Tensile Stress ² (Yield)	10.0	МРа	ISO 37		
Tensile Elongation ³ (Break)	700	%	ISO 37		
Tear Strength ⁴	21	kN/m	ISO 34-1		
Compression Set ⁵			ISO 815		
23°C, 72 hr	28	%			

70°C, 24 hr	45	%		
100°C, 24 hr	69	%		
Injection	Nominal Value	Unit		
Drying Temperature	60.0 to 80.0	°C		
Drying Time	2.0 to 4.0	hr		
Rear Temperature	180	°C		
Middle Temperature	200	°C		
Front Temperature	220	°C		
Mold Temperature	25.0 to 40.0	°C		
Injection Pressure	20.0 to 100	MPa		
Back Pressure	2.00 to 10.0	MPa		
NOTE				
1.	Injection Pressure: 70.0 bar	Injection Pressure: 70.0 bar		
2.	Type S2, 200 mm/min			
3.	Type S2, 200 mm/min			
4.	Method Bb, Angle (Nicked)			
5.	Method A			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

