

GERMAMID 6 GF 30

Polyamide 6

Kunststoff-Kontor-Hamburg GmbH

Message:

GERMAMID 6 GF 30 is a Polyamide 6 (Nylon 6) material filled with 30% glass fiber. It is available in Europe.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm ³	ISO 1183
Molding Shrinkage	0.015 to 1.0	%	ISO 294-4
Water Absorption (Saturation, 23°C)	2.0	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9000	MPa	ISO 527-2
Tensile Stress (Yield)	180	MPa	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Flexural Stress	250	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	13	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	60	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	215	°C	ISO 75-2/B
Melting Temperature	218	°C	
Thermal Conductivity	0.28	W/m/K	ISO 8302
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+12	ohms	IEC 60093

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT