

KOPLA PA6 KNT1030

Polyamide 6

KOPLA Co., Ltd.

Message:

KOPLA PA6 KNT1030 is a Polyamide 6 (Nylon 6) material filled with mineral. It is available in Asia Pacific.

Important attributes of KOPLA PA6 KNT1030 are:

Flame Rated

Good Dimensional Stability

Typical application of KOPLA PA6 KNT1030: Automotive

General Information			
Filler / Reinforcement	Mineral		
Features	Good Dimensional Stability		
Uses	Automotive Exterior Parts		
	Automotive Under the Hood		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.38	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.30 to 0.90	%	ASTM D955
Water Absorption (23°C, 24 hr)	1.1	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	78.5	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	5.0	%	ASTM D638
Flexural Modulus (23°C)	5390	MPa	ASTM D790
Flexural Strength (23°C)	118	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	59	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	200	°C	
1.8 MPa, Unannealed	150	°C	
Melting Temperature	220	°C	
CLTE - Flow	4.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+13 to 1.0E+15	ohms · cm	ASTM D257
Dielectric Strength	22	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	4.00		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

