

# Beetafin® RV9009

Polyurethane (Polyester based)

BIP (Oldbury) Limited

## Message:

Beetafin® RV9009 is a Polyurethane (Polyester based) (PUR-Ester) product. It is available in Europe.

| General Information             |               |      |
|---------------------------------|---------------|------|
| Physical                        | Nominal Value | Unit |
| pH                              | 8.0           |      |
| Solids Content                  | 40            | %    |
| Solvent Content                 | 9% NEP        |      |
| Konig Hardness                  | 12.0          | sec  |
| Films                           | Nominal Value | Unit |
| Secant Modulus - 100%, MD       | 3.50          | MPa  |
| Tensile Strength                | 25.0          | MPa  |
| Tensile Elongation - MD (Break) | 1000          | %    |
| Thermal                         | Nominal Value | Unit |
| Vicat Softening Temperature     | 125           | °C   |
| Uncured Properties              | Nominal Value | Unit |
| Viscosity                       | 0.15          | Pa·s |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

