Kuraray CP-Polymer CP-4104 MI

Polyvinyl Alcohol

Kuraray Co., Ltd.

Message:

Melt moldable grades

General Information			
Features	Biodegradable		
	Water Soluble		
Forms	Granules		
Physical	Nominal Value	Unit	
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	75 to 80	g/10 min	
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	55.0	°C	DSC
Melting Temperature	210	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

