

Fortron® ICE 506L

Polyphenylene Sulfide

Celanese Corporation

Message:

Fortron ICE 506L is a faster crystallizing version of Fortron 1140L6. It offers essentially the same characteristics of 1140L6 with improved crystallization efficiency for faster cycle times in complex geometries.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 40% filler by weight		
Features	Fast molding cycle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.60	g/cm ³	ASTM D792
--	1.65	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)	19	g/10 min	ASTM D1238
Molding Shrinkage			
Flow	0.20 - 0.30	%	ASTM D955
Transverse flow	0.50 - 0.70	%	ASTM D955
Vertical flow direction	0.40 - 0.60	%	ISO 294-4
Flow direction	0.20 - 0.60	%	ISO 294-4
Water Absorption (Saturation, 23°C)	0.020	%	ISO 62
Spiral Flow	21.5		Internal method
Specific Heat Capacity of Melt	1500	J/kg/°C	Internal method
CSA Rating - F-1 (840.0 µm)	A00		
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
Class m	100		ASTM D785
M scale	100		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	14700	MPa	ISO 527-2/1A/1
Tensile Strength			
Fracture, 23°C	200	MPa	ASTM D638
Fracture	195	MPa	ISO 527-2/1A/5
Tensile Elongation			
Fracture, 23°C	2.0	%	ASTM D638
Fracture	1.9	%	ISO 527-2/1A/5
Flexural Modulus (23°C)	14500	MPa	ISO 178
Flexural Stress	285	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA

-30°C	10	kJ/m ²	ISO 179/1eA
23°C	10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	53	kJ/m ²	ISO 179/1eU
23°C	53	kJ/m ²	ISO 179/1eU
Notched Izod Impact			ISO 180/1A
-30°C	10	kJ/m ²	ISO 180/1A
23°C	10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	34	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, not annealed	280	°C	ASTM D648
1.8 MPa, not annealed	265	°C	ASTM D648
1.8 MPa, not annealed	270	°C	ISO 75-2/A
8.0 MPa, not annealed	215	°C	ISO 75-2/C
Glass Transition Temperature ¹	90.0	°C	ISO 11357-2
Melting Temperature ²	280	°C	ISO 11357-3
Linear thermal expansion coefficient			ISO 11359-2
Flow	2.6E-5	cm/cm/°C	ISO 11359-2
Lateral	4.2E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity			
--	1.0E+16	ohms·cm	ASTM D257
--	> 1.0E+15	ohms·cm	IEC 60093
Dielectric Strength			
-- ³	15	kV/mm	ASTM D149
--	28	kV/mm	IEC 60243-1
Dielectric Constant			
1 kHz	3.50		ASTM D150
1 MHz	3.50		ASTM D150
1 MHz	4.10		IEC 60250
Dissipation Factor			
1 kHz	1.0E-3		ASTM D150
1 MHz	1.0E-3		ASTM D150
1 MHz	2.0E-3		IEC 60250
Arc Resistance	134	sec	ASTM D495
Comparative Tracking Index	125	V	IEC 60112
Injection	Nominal Value	Unit	
Drying Temperature	130 - 140	°C	
Drying Time	3.0 - 4.0	hr	
Suggested Max Moisture	0.020	%	

Hopper Temperature	20.0 - 30.0	°C
Rear Temperature	290 - 300	°C
Middle Temperature	310 - 320	°C
Front Temperature	330 - 340	°C
Nozzle Temperature	310 - 330	°C
Processing (Melt) Temp	330 - 340	°C
Mold Temperature	90.0 - 160	°C
Injection Pressure	50.0 - 100	MPa
Injection Rate	Fast	
Holding Pressure	30.0 - 70.0	MPa
Back Pressure	0.00 - 3.00	MPa
Screw Speed	50 - 120	rpm

Injection instructions

Manifold Temperature: 330 to 340°C Zone 4 Temperature: 330 to 340°C Feed Temperature: 60 to 80°C

NOTE

- 10°C/min
- 10°C/min
- Method A (short time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

