

DEXFLEX® 727-UV BTFA ADOBE

Polypropylene

LyondellBasell Industries

Message:

Dexflex 727-UV BTFA ADOBE very high melt flow, medium flexural modulus, UV-stabilized, mineral-filled, thermoplastic elastomeric olefin has an excellent balance of properties and processability.

General Information		
Filler / Reinforcement	Mineral filler	
Features	Workability, good	
	High liquidity	
Processing Method	Injection molding	
Physical	Nominal Value	Unit
Density (23°C)	0.900	g/cm ³
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	19	g/10 min
Mechanical	Nominal Value	Unit
Flexural Modulus - 1% Secant ¹	850	MPa
NOTE		
1.	Program A, 1.3mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT