Chemraz 551

Perfluoroelastomer

Greene, Tweed & Co.

Message:

Chemraz 551 is a Perfluoroelastomer product. It is available in North America. Applications of Chemraz 551 include engineering/industrial parts and sealing applications. Characteristics include: Chemical Resistant Heat Resistant

| General Information | | | |
|---|---------------------------------|-------|-------------|
| Features | Good Chemical Resistance | | |
| | High Heat Resistance | | |
| | | | |
| Uses | Gaskets | | |
| | Seals | | |
| | Semiconductor Molding Compounds | | |
| | | | |
| Appearance | Black | | |
| Forms | Pellets | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 2.00 | g/cm³ | ASTM D792 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A) | 80 | | ASTM D2240 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Stress | | | ASTM D1414 |
| 50% Strain | 3.10 | MPa | |
| 100% Strain | 10.2 | MPa | |
| Tensile Strength (Break) | 23.6 | MPa | ASTM D1414 |
| Tensile Elongation (Break) | 180 | % | ASTM D1414 |
| Compression Set ¹ (204°C, 70 hr) | 20 | % | ASTM D395 |
| Thermal | Nominal Value | Unit | |
| Service Temperature | -12 to 316 | °C | |
| NOTE | | | |
| 1. | 25% Deflection | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

