

# Fluorosite 300 - GML

Polytetrafluoroethylene

UNIFLON

## Message:

Fluorosite 300-GML is a polytetrafluoroethylene (PTFE) product. It can be processed by sintering or injection molding and is available in North America or Latin America.

General Information			
Additive	Unspecified additive		
Features	Low liquidity		
Processing Method	Sintering		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	3.10 - 3.14	g/cm <sup>3</sup>	Internal method
Contractility-Sintering	1.4 - 2.5	%	Internal method
Sintering Temperature - Maximum	365	°C	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	65 - 72		Internal method
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength	26.0	MPa	Internal method
Tensile Elongation (Break)	190	%	Internal method
Additional Information	Nominal Value	Unit	
Code: 010031901			
Injection	Nominal Value	Unit	
Mold Temperature	21.0 - 25.0	°C	
Injection Pressure	44.1 - 53.9	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT