

WanBlend® WHT-THF9465T2

Thermoplastic Polyurethane Elastomer (Polyester)

Wanhua Chemical Group Co., Ltd.

Message:

WHT-THF9465T2 is polyester-based flame retardant thermoplastic Polyurethane (TPU) compound, supplied in form of transparent, translucent pellets, which combine the zero halogen objective with excellent mechanical properties and processability.

Applications:

Extrusion - wire and cable

General extrusion and injection molding where flame retardant properties are required.

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
	Good Processability		
	Halogen Free		
Uses	Wire & Cable Applications		
Appearance	Clear/Transparent		
	Translucent		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	62 to 68		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% Strain	6.80	MPa	
300% Strain	14.0	MPa	
Tensile Strength	34.7	MPa	ASTM D412
Tensile Elongation (Break)	650	%	ASTM D412
Tear Strength	70.0	kN/m	ASTM D624
Flammability	Nominal Value		Test Method
Flame Rating	V-2		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 100	°C	
Drying Time	2.0 to 3.0	hr	
Rear Temperature	185	°C	

Middle Temperature	195	°C
Front Temperature	200	°C
Nozzle Temperature	205	°C
Injection Pressure	65.0	MPa
Extrusion	Nominal Value	Unit
Drying Temperature	90.0 to 100	°C
Drying Time	3.0 to 4.0	hr
Cylinder Zone 1 Temp.	180	°C
Cylinder Zone 3 Temp.	190	°C
Cylinder Zone 5 Temp.	200	°C
Die Temperature	195	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

