# Lotryl® 35BA40

### Ethylene Butyl Acrylate Copolymer

#### Arkema

#### Message:

LOTRYL® 35BA40 is a random copolymer of Ethylene and Butyl Acrylate produced by high-pressure radicalar polymerization process. Applications

Due to the high butyl acrylate content, LOTRYL® 35BA40 can be used for applications where flexibility and polarity are required. Combined with a high fluidity, LOTRYL® 35BA40 is particularly recommended for the formulation of hot melt adhesives. It can also be used as processing-aid in highly filled compounds.

General Information			
Features	Random Copolymer		
Uses	Adhesives		
	Film		
	Plastics Modification		
Processing Method	Blown Film		
	Cast Film		
Physical	Nominal Value	Unit	Test Method
Density	0.930	g/cm³	ISO 1183, ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16			
kg)	35 to 45	g/10 min	ASTM D1238, ISO 1133
n-Butyl Acrylate Content	33.0 to 37.0	wt%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A,	70		4 CTM D0040 100 000
Compression Molded)	70		ASTM D2240, ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break, Compression Molded)	2.00	МРа	ASTM D638, ISO 527-2
Tensile Elongation (Break, Compression			
Molded)	600	%	ASTM D638, ISO 527-2
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	< 40.0	°C	ISO 306/A, ASTM D1525 <sup>1</sup>
Melting Temperature	66.0	°C	ISO 11357-3
Ring and Ball Softening Point	110	°C	ASTM E28
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	150 to 170	°C	
Cylinder Zone 2 Temp.	170	°C	
Cylinder Zone 3 Temp.	170	°C	
Cylinder Zone 4 Temp.	170	°C	
Die Temperature	170	°C	
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

