

WONDERLITE® PC-6600

Polycarbonate
CHI MEI CORPORATION

Message:
PC, Non-halogen Flame Retardant, available in translucent

General Information			
UL YellowCard	E194560-101989114		
Features	Flame Retardant		
	Halogen Free		
RoHS Compliance	RoHS Compliant		
Appearance	Translucent		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C)	122		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	61.8	MPa	ASTM D638
Tensile Elongation ² (Break)	100	%	ASTM D638
Flexural Modulus ³	2350	MPa	ASTM D790
Flexural Strength ⁴	90.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 0.125 mm)	780	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load ⁵ (1.8 MPa, Unannealed)	125	°C	ASTM D648
Vicat Softening Temperature	143	°C	ASTM D1525 ⁶
Flammability	Nominal Value		Test Method
Flame Rating (1.10 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	4.0	hr	
Rear Temperature	270 to 300	°C	
Middle Temperature	270 to 300	°C	
Front Temperature	270 to 300	°C	
Mold Temperature	70.0 to 100	°C	

NOTE	
1.	50 mm/min
2.	50 mm/min
3.	1.3 mm/min
4.	1.3 mm/min
5.	120°C/hr
6.	Rate A (50°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

