

Aquivion® PW87S

Perfluorosulfonic Acid

Solvay Specialty Polymers

Message:

Aquivion® PW87S is a coarse, acid powder based on the short-side-chain (SSC) copolymer of Tetrafluoroethylene and the Sulfonyl Fluoride Vinyl Ether (SFVE) $\text{CF}_2=\text{CF}-\text{O}-(\text{CF}_2)_2-\text{SO}_2\text{F}$ produced by Solvay. The resulting perfluoropolymer's functional groups are in their sulfonic acid form, SO_3H . Aquivion® PW87S is chemically-stabilized (denoted by the S-suffix).

Aquivion® PW87S exhibits ionic exchange capacity and it can be used as is under conditions where conventional exchange resins have shown insufficient chemical resistance.

Due to its superacid functionality with many active groups, it can be used either directly or as an ingredient of composite structures active as a heterogeneous catalyst. This encompasses a wide range of organic syntheses and respective reaction mechanisms.

PW87S is a good trade-off between polymer crystallinity and ionic exchange capacity. It is insoluble in water, acid or bases and in most solvents unless extreme conditions would be applied.

Furthermore, Aquivion® PW87S can be dissolved in some organic solvents to produce ion exchange capacity membrane. Proper organic solvents are dipolar aprotic such as N-ethyl-2-pyrrolidone (NEP) and dimethyl sulfoxide. To facilitate the dissolution slightly increase the temperature to 50-60°C.

General Information			
Appearance	White		
Forms	Powder		
Physical	Nominal Value	Unit	Test Method
Equivalent (EW) ¹	840 - 900	g/eq	Internal method
Moisture Content	5.0	wt%	
Total acid content	1.11 - 1.19	meq/g	Internal method
Additional Information			
HEALTH, SAFETY AND ENVIRONMENT			
Aquivion® powders are not harmful if used and handled according to standard processing procedures (see for example 'the Guide to the Safe Handling of Fluoropolymer Resins' issued by the Society of the Plastics Industry). If handled inappropriately, membranes may release harmful toxic chemicals. Please refer to corresponding Material Safety Data Sheets for more information on handling and safety.			
PACKAGING, SHIPMENT AND STORAGE			
Aquivion® powders are delivered in standard polypropylene bottles and drums. Products should be kept closed in their original packaging.			
NOTE			
1.	eq = mol SO_3H		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT