

GLAMIDE® T-663G30

Polyamide 66

TOYOBO America, Inc.

Message:

GLAMIDE®T-663G30 is a polyamide 66 (nylon 66) product, which contains a 30% glass fiber reinforced material. It is available in North America. The main characteristics are: flame retardant/rated flame.

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 30% filler by weight		
Forms		Particle		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.37	--	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	7.0	--	g/10 min	ASTM D1238
Molding Shrinkage - Flow				ASTM D955
1.00 mm	0.20 - 0.50	--	%	ASTM D955
3.00 mm	0.60 - 0.90	--	%	ASTM D955
Water Absorption				ASTM D570
24 hr	0.60	--	%	ASTM D570
Equilibrium, 65% RH	1.7	--	%	ASTM D570
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (R-Scale)	121	--		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength				ASTM D638
Yield, -40°C	235	215	MPa	ASTM D638
Yield, 23°C	195	145	MPa	ASTM D638
Yield, 80°C	120	100	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	3.2	3.9	%	ASTM D638
Flexural Modulus				ASTM D790
-40°C	10800	9800	MPa	ASTM D790
23°C	8700	5800	MPa	ASTM D790
80°C	5400	4000	MPa	ASTM D790
Flexural Strength				ASTM D790
Yield, -40°C	315	300	MPa	ASTM D790
Yield, 23°C	280	210	MPa	ASTM D790
Yield, 80°C	185	130	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact				ASTM D256
-40°C	70	80	J/m	ASTM D256
23°C	110	140	J/m	ASTM D256

Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ASTM D648
0.45 MPa, not annealed	262	--	°C	ASTM D648
1.8 MPa, not annealed	255	--	°C	ASTM D648
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+15	1.0E+13	ohms·cm	ASTM D257
Dielectric Strength (2.00 mm)	26	20	kV/mm	ASTM D149
Dielectric Constant (1 kHz)	4.10	--		ASTM D150
Arc Resistance	100	92.0	sec	ASTM D495
Comparative Tracking Index	575	575	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating	HB	--		UL 94

Additional Information

调节后的

Volume Resistivity, ASTM D257: 1e10 to 1e11 ohm-m

Injection	Dry	Unit
Processing (Melt) Temp	280 - 310	°C
Mold Temperature	60.0	°C
Injection Pressure	30.0 - 60.0	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT