

Tekuform H13

Acetal (POM) Copolymer
TEKUMA Kunststoff GmbH

Message:

Tekuform H13 is a polyoxymethylene (POM) copolymer material. This product is available in Europe.

General Information			
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR)	12.0	cm ³ /10min	ISO 1133
Molding Shrinkage	1.7 - 2.0	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3200	MPa	ISO 527-2
Tensile Stress (Yield)	14.0	MPa	ISO 527-2
Tensile Strain (Yield)	220	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
30°C	8.0	kJ/m ²	ISO 179/1eA
230°C	9.0	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	95.0	°C	ISO 75-2/A
Additional Information			
Tensile Strain at Yield, ISO 527: 205 to 225%			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT