DAPCO™ 3008

Epoxy; Epoxide

Cytec Industries Inc.

Message:

DAPCO™ 3008 is a two-component, self-extinguishing epoxy filler.

Features & Benefits:

Cure at room temperature

Excellent adhesion to metal and wood

Very low water absorption

Good chemical resistance, especially to aircraft fluids

Can be nailed, threaded, countersunk, drilled, cut, etc. without cracking or chipping

100% solids

FAR 25.853

Suggested Applications:

DAPCO 3008 is commonly used for potting, stiffening and edge filling in honeycomb core.

| General Information | | | |
|------------------------------|--------------------------|-------|--|
| Features | Good Adhesion | | |
| | Good Chemical Resistance | | |
| | High Stiffness | | |
| | Humidity Resistant | | |
| | Low Density | | |
| | Self Extinguishing | | |
| | | | |
| Uses | Adhesives | | |
| | Aerospace Applications | | |
| | Filling Applications | | |
| | Structural Parts | | |
| | | | |
| Agency Ratings | FAR 25.853 | | |
| Appearance | Yellow | | |
| Forms | Paste | | |
| Processing Method | Potting | | |
| Physical | Nominal Value | Unit | |
| Specific Gravity | 0.449 to 0.513 | g/cm³ | |
| Water Absorption (24 hr) | 0.40 | % | |
| Hardness | Nominal Value | Unit | |
| Durometer Hardness (Shore D) | 60 | | |
| Mechanical | Nominal Value | Unit | |
| Flexural Modulus | 1380 | MPa | |
| Compressive Strength | 20.7 | MPa | |
| Flammability | Nominal Value | | |
| Flammability ¹ | Self-extinguishing | | |

| Thermoset | Nominal Value |
|----------------------|--------------------------|
| Thermoset Components | |
| Hardener | Mix Ratio by Weight: 35 |
| Resin | Mix Ratio by Weight: 100 |
| NOTE | |
| 1 | 3 seconds |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

