

INDURE™ X76-UV 4WFA

Polyolefin

LyondellBasell Industries

Message:

Indure X76-UV 4WFA engineered polyolefin material is typically used for various automotive exterior-trim applications. It offers an excellent combination of scratch resistance, UV resistance, high-gloss part appearance, good processability and a balance of stiffness and impact resistance.

General Information			
Features	Rigid, good		
	Highlight		
	Impact resistance, good		
	Good UV resistance		
	Workability, good		
	Scratch resistance		
	ductility		
Uses	Car anti-collision bar		
	Application in Automobile Field		
	Automotive exterior parts		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	35	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 4.00 mm)	20.0	MPa	ISO 527-2/50
Flexural Modulus ¹ (4.00 mm)	950	MPa	ISO 178
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT