

SEQUEL® 1825

Thermoplastic Polyolefin Elastomer

LyondellBasell Industries

Message:

Sequel 1825 thermoplastic polyolefin is designed for automotive and heavy-truck applications that require energy management combined with ductility, stiffness and impact resistance over a broad temperature range. This material exhibits excellent processability and dimensional stability

Typical Customer Applications:

Exterior Applications, Bumpers

General Information			
Features	Ductile		
	Good Dimensional Stability		
	Good Impact Resistance		
	Good Processability		
	Good Stiffness		
Uses	Automotive Applications		
	Automotive Bumper		
	Automotive Exterior Parts		
Physical	Nominal Value	Unit	Test Method
Density	1.16	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)	15	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress ¹ (Yield)	20.0	MPa	ISO 527-2
Flexural Modulus ²	2500	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Instrumented Dart Impact	16.5	J	ASTM D3763
NOTE			
1.	150x10x4 mm specimen		
2.	80x10x4mm specimen		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT