

ULTEM™ 1000P resin

Polyether Imide
SABIC Innovative Plastics

Message:
Standard flow Polyetherimide (Tg 217C) in 350 micron powder. ECO Conforming.

General Information			
Features	ECO Compliant		
Agency Ratings	EU Eco		
Forms	Powder		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.27	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (337°C/6.6 kg)	9.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.70	%	Internal Method
Water Absorption			ASTM D570
24 hr	0.25	%	
Equilibrium, 23°C	1.3	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	109		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	3590	MPa	ASTM D638
Tensile Strength ² (Yield)	110	MPa	ASTM D638
Tensile Elongation ³			ASTM D638
Yield	7.0	%	
Break	60	%	
Flexural Modulus ⁴ (100 mm Span)	3310	MPa	ASTM D790
Flexural Strength ⁵ (Yield, 100 mm Span)	152	MPa	ASTM D790
Poisson's Ratio	0.36		ASTM D638
Taber Abrasion Resistance (1000 Cycles, 1000 g, CS-17 Wheel)	10.0	mg	ASTM D1044
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	53	J/m	ASTM D256
Unnotched Izod Impact (23°C)	1300	J/m	ASTM D4812
Gardner Impact (23°C)	36.6	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 6.40 mm	210	°C	
1.8 MPa, Unannealed, 6.40 mm	201	°C	
Vicat Softening Temperature	219	°C	ASTM D1525 ⁶

CLTE			ASTM E831
Flow : -20 to 150°C	5.6E-5	cm/cm/°C	
Transverse : -20 to 150°C	5.4E-5	cm/cm/°C	
Thermal Conductivity	0.22	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+17	ohms·cm	ASTM D257
Dielectric Strength			ASTM D149
1.60 mm, in Air	33	kV/mm	
1.60 mm, in Oil	28	kV/mm	
Dielectric Constant (1 kHz)	3.15		ASTM D150
Dissipation Factor			ASTM D150
1 kHz	1.3E-3		
2.45 GHz	2.5E-3		
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	47	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature	149	°C	
Drying Time	4.0 to 6.0	hr	
Drying Time, Maximum	24	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 to 60	%	
Rear Temperature	332 to 399	°C	
Middle Temperature	338 to 399	°C	
Front Temperature	343 to 399	°C	
Nozzle Temperature	343 to 399	°C	
Processing (Melt) Temp	349 to 399	°C	
Mold Temperature	135 to 163	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	40 to 70	rpm	
Vent Depth	0.025 to 0.076	mm	
NOTE			
1.	5.0 mm/min		
2.	Type I, 5.0 mm/min		
3.	Type I, 5.0 mm/min		
4.	2.6 mm/min		
5.	2.6 mm/min		
6.	Rate B (120°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

