

# Optix® CA-41 UVT

Polymethyl Methacrylate Acrylic

Plaskolite, Inc.

## Message:

Optix® CA-41 UVT is a polymethyl methacrylate-acrylic material. This product is available in North America or Europe.

| General Information                                     |               |          |             |
|---------------------------------------------------------|---------------|----------|-------------|
| Physical                                                | Nominal Value | Unit     | Test Method |
| Melt Mass-Flow Rate (MFR)                               | 26            | g/10 min | ASTM D1238  |
| Molding Shrinkage - Flow                                | 0.20 - 0.60   | %        | ASTM D955   |
| Hardness                                                | Nominal Value | Unit     | Test Method |
| Rockwell Hardness (M-Scale)                             | 74            |          | ASTM D785   |
| Mechanical                                              | Nominal Value | Unit     | Test Method |
| Tensile Modulus                                         | 2810          | MPa      | ASTM D638   |
| Tensile Strength                                        | 53.8          | MPa      | ASTM D638   |
| Tensile Elongation (Break)                              | 2.4           | %        | ASTM D638   |
| Flexural Strength                                       | 80.7          | MPa      | ASTM D790   |
| Impact                                                  | Nominal Value | Unit     | Test Method |
| Notched Izod Impact                                     | 16            | J/m      | ASTM D256   |
| Dart Drop Impact <sup>1</sup> (3.18 mm)                 | 0.226         | J        | ASTM D5420  |
| Thermal                                                 | Nominal Value | Unit     | Test Method |
| Deflection Temperature Under Load (1.8 MPa, Unannealed) | 72.8          | °C       | ASTM D648   |
| Vicat Softening Temperature                             | 90.0          | °C       | ASTM D1525  |
| CLTE - Flow (-30 to 30°C)                               | 6.0E-5        | cm/cm/°C | ASTM D696   |
| NOTE                                                    |               |          |             |
| 1.                                                      | Geometry GB   |          |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT