

Clearflex® CL B0

Very Low Density Polyethylene

Versalis S.p.A.

Message:

Clearflex CL B0 is a linear low density polyethylene, with antioxidants, characterised by a very low density (VLDPE).

The resin has a high stretchability and a good cling effect.

Main Application

Clearflex CL B0 is recommended for applications in which soft touch and flexibility are required, for the improvement of impact resistance when used as additive in blend with other polyolefins formulated with or without mineral fillers. Clearflex CL B0 is also used as cling agent in stretch film.

General Information			
Additive	Antioxidant		
Features	Antioxidant		
	Food Contact Acceptable		
	Good Flexibility		
	Good Stretchability		
	High Cling		
	Low Density		
	Soft		
Uses	Blending		
	Film		
	Soft Touch Applications		
Agency Ratings	EU Food Contact, Unspecified Rating		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.911	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction (vs. Itself - Dynamic, Cast Film)	> 0.50		ISO 8295
Films	Nominal Value	Unit	Test Method
Film Thickness - Recommended / Available	8 to 50µm		
Tensile Modulus			ISO 527-3
1% Secant, MD : Cast Film	80.0	MPa	
1% Secant, TD : Cast Film	90.0	MPa	
Tensile Stress			ISO 527-3
MD : Yield, Cast Film	7.00	MPa	
TD : Yield, Cast Film	7.00	MPa	
MD : Break, Cast Film	32.0	MPa	

TD : Break, Cast Film	20.0	MPa	
Tensile Elongation			ISO 527-3
MD : Break, Cast Film	500	%	
TD : Break, Cast Film	700	%	
Dart Drop Impact ¹ (Cast Film)	120	g	ISO 7765-1
Elmendorf Tear Strength ²			ISO 6383-2
MD	35.0	kN/m	
TD	100.0	kN/m	
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -70.0	°C	ASTM D746
Vicat Softening Temperature	80.0	°C	ISO 306/A
Melting Temperature	118	°C	Internal Method
Optical	Nominal Value	Unit	Test Method
Gloss (45°, Cast Film)	70		ASTM D2457
Haze (Cast Film)	6.0	%	ISO 14782
Extrusion	Nominal Value	Unit	
Melt Temperature	220 to 270	°C	
NOTE			
1.	F50		
2.	Cast Film		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

