Geon™ Vinyl Flexible R1480E

Flexible Polyvinyl Chloride

PolyOne Corporation

Message:

Geon™Vinyl Flexible R1480E is a flexible polyvinyl chloride product. It can be processed by extrusion coating and is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Typical application areas are: wire and cable.

Features include

Flame Retardant

Stable

| General Information | | | |
|---|--|-------|--------------------|
| Additive | Lead stabilizer | | |
| Features | Flame retardancy | | |
| Uses | Wire and cable applications | | |
| | Communication wire insulation material | | |
| | | | |
| Forms | Particle | | |
| Processing Method | Extrusion coating | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.32 | g/cm³ | ASTM D792 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A, 15 sec) | 95 | | ASTM D2240 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength ¹ (Break) | 20.7 | МРа | ASTM D638 |
| Tensile Elongation ² (Break) | 290 | % | ASTM D638 |
| Aging | Nominal Value | Unit | |
| Tensile strength retention rate ³ (100°C, | | | |
| 1.91 mm) | 85 | % | |
| Elongation retention rate ⁴ (100°C, 1.91 mm) | 100 | % | |
| Thermal | Nominal Value | Unit | Test Method |
| Brittleness Temperature | -17.0 | °C | ASTM D746 |
| UL Temperature Rating | 60 | °C | 7.51W <i>D1</i> 40 |
| Flammability | Nominal Value | Unit | Test Method |
| Oxygen Index (1.91 mm) | 26 | % | ASTM D2863 |
| Additional Information | | | , 5 52503 |
| 注释:模制厚板(0.075")的典型属性;不能视为 | 技术规格 | | |
| Extrusion | Nominal Value | Unit | |
| Melt Temperature | 170 - 180 | °C | |
| NOTE | | | |
| 1. | Type 4, 510mm/min | | |
| 2. | Type 4, 510mm/min | | |
| | . , pc ¬, 5 romm/nm | | |

4. 168 hours, UL standard

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

