

Lifocork® TO 751004-4

Ethylene Vinyl Acetate Copolymer

ELASTO

Message:

The main quantity of natural cork which is harvested today is used as pressed cork or mixed with PU or rubber. The processing of this kind of cork can be expensive and require a lot of energy.

We have developed a special manufacturing method to combine natural cork with thermoplastic raw materials. Meaning Lifocork can be processed using typical thermoplastic processing methods such as injection moulding, extrusion or thermoforming.

Cork is a natural product which comes from the bark of the cork oak tree. The removal of the bark does not harm the trees and the bark is only harvested after the first 20 years of growth. The removal stimulates a steady regeneration of the bark. Each cork tree provides on average 16 harvests over its 150-200 year lifespan.

Cork itself has a cell-like structure which is light and highly compressible. It is used in construction, sports, industrial and household applications.

It's also possible to make foamed parts from Lifocork. This offers materials with very low densities (as low as 0.45 g/ccm) and therefore gives lightweight parts. The foamed Lifocork also gives a damping, shock absorbent effect, ideal for orthopaedic shoe lifts and inserts.

Lifocork can be processed using thermoplastic processing methods. In injection moulding it can be processed using standard equipment.

Lifocork can also be processed in 2-component moulding. It has an excellent bond to TPE, PP and PE.

Other processing methods include extrusion or thermoforming with a double belt press.

General Information			
Filler / Reinforcement	Cork		
Features	Low density		
	Moisture resistance		
	Good UV resistance		
	Foamable property		
	Updatable resources		
	Workability, good		
	Good wear resistance		
Uses	Handle		
	Power/other tools		
	Household goods		
	Soft handle		
	Sporting goods		
	Toys		
Processing Method	Co-extrusion molding		
	Extrusion		
	Thermoforming		
	Injection molding		
Hardness	Nominal Value		Test Method
Durometer Hardness (Shore A)	85		DIN 53505
Injection	Nominal Value		Unit
Rear Temperature	150	°C	

Middle Temperature	160	°C
Front Temperature	170	°C
Nozzle Temperature	175	°C
Injection Rate	Slow	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

