

Algoflon® D 1610 F

Polytetrafluoroethylene

Solvay Specialty Polymers

Message:

Algoflon® D 1610 F is a PFOA-free white aqueous PTFE dispersion. It is designed for additivation of plastics and is particularly recommended for use as anti-drip in flame retardant formulations.

Algoflon® D 1610 F exhibits good wetting properties and shear stability.

Main features of Algoflon® D 1610 F PTFE dispersion are:

NO polyethoxylated alkylphenols

Very good wetting properties

Good shear stability

Excellent anti-dripping effect

General Information			
Features	Low friction coefficient		
	Good chemical resistance		
	Heat resistance, high		
Uses	Impregnation uses		
	Additive		
Appearance	White		
Forms	Latex		
Physical	Nominal Value	Unit	Test Method
pH	> 9.0		ASTM D4441
Density	1.510	g/cm ³	ASTM D4441
Average Particle Size	250	nm	Internal method
PTFE content-(On the mixture)	60.0	wt%	ASTM D4441
Nonionic surfactant-(On the mixture)	3.5	wt%	ASTM D4441
Additional Information	Nominal Value	Unit	Test Method

Processing

Algoflon® D 1610 F can be processed undiluted or diluted using distilled or deionized water.

Storage and Handling

Algoflon® PTFE dispersions must be stored under suitable temperature conditions to ensure prolonged stability. Temperatures lower than 5°C must be avoided to prevent irreversible settling. Also, some settling may occur on prolonged standing and/or heat exposure. It is therefore strongly recommended that the product is always kept at temperatures below 35°C. The optimum storage temperature range is 10-25°C. It is also advisable that the product is homogenized by gentle rolling or stirring once per month and prior to use.

Safety and Toxicology

Before using Algoflon® PTFE dispersions consult the product Material Safety Data Sheet and follow all label directions and handling precautions. As with all PTFE materials, handling and processing should only be carried out in well ventilated areas. Venting units should be installed above processing equipment. Fumes must not be inhaled and eye and skin contact ought to be avoided. In case of skin contact wash with soap and water. In case of eye contact flush with water immediately and seek medical help. Do not smoke in areas contaminated with powder, vapor or fumes. See Material Safety Data Sheet for detailed advice on waste disposal methods

Packaging

Algoflon® D 1610 F is packaged in either 30 kg drums or 1500 kg IBC's.

Additional Technical Information

For Material Safety Data Sheet or additional technical information consult your Solvay Specialty Polymers sales representative.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

