

Pro PP-HO-20T

Polypropylene Homopolymer
Pro Polymers

Message:

PP-HO-20T is a 20% Talc Filled, Polypropylene Homopolymer.

General Information			
Filler / Reinforcement	Talc filler, 20% filler by weight		
Features	Homopolymer		
Uses	Battery box		
	Electrical appliances		
	Furniture		
	Shell		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.06	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow: 3.18mm	1.1	%	ASTM D955
Transverse flow: 3.18mm	1.1	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	74		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	33.0	MPa	ASTM D638
Flexural Modulus	2410	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	27	J/m	ASTM D256
Dart Drop Impact	0.900	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	120	°C	ASTM D648
1.8 MPa, not annealed	69.0	°C	ASTM D648
Additional Information			

Melt Flow Rate, ASTM D1238, 230°C/2.1kgf: 8 to 12 g/10 min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

