

# ULTEM™ foam XP080

Polyether Imide

SABIC Innovative Plastics

## Message:

ULTEM foam is a polyetherimide based thermoplastic foam with excellent flame, smoke and toxicity performance. The material combines a high strength to weight ratio with low moisture absorption. The foam also possesses excellent dielectric properties. ULTEM foam is targeted at applications where structural fire performance, radar transparency, or extreme hot or cold environments are required. ULTEM foam is thermoformable and compatible with phenolic pre-pregs. Information on processing or secondary operations is available upon request.

General Information			
Features	Flame Retardant		
	Good Electrical Properties		
	High Heat Resistance		
	High Strength		
	Low Moisture Absorption		
	Low Smoke Emission		
	Low Temperature Resistant		
	Non-Toxic		
Uses	Foam		
Physical	Nominal Value	Unit	Test Method
Density	0.0800	g/cm <sup>3</sup>	ASTM D1622
Water Absorption (Equilibrium)	4.0	%	ASTM D272
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>1</sup>	37.0	MPa	ASTM D638
Tensile Strength <sup>2</sup>	1.70	MPa	ASTM D638
Compressive Modulus <sup>3</sup>	71.0	MPa	ASTM D1621
Compressive Strength <sup>4</sup>	1.20	MPa	ASTM D1621
Shear Modulus	19.0	MPa	ASTM C273
Shear Strength	1.00	MPa	ASTM C273
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength	0.80	kJ/m <sup>2</sup>	ISO 179
Thermal	Nominal Value	Unit	Test Method
Thermal Conductivity	0.037	W/m/K	ASTM C518
Flammability	Nominal Value	Unit	Test Method
Insulation Radiant Panel	PASSES		FAR 25.853
OSU Peak Heat Release Rate <sup>5</sup>	< 55.0	kW/m <sup>2</sup>	FAR 25.853
OSU Total Heat Release <sup>6</sup>	< 55.0	kW · min/m <sup>2</sup>	FAR 25.853
Smoke Density	< 10	Ds	FAR 25.853
Smoke Toxicity			Internal Method
OEM ABD	PASSES		


OEM BSS	PASSES	
Vertical Burn - 60 second	PASSES	FAR 25.853
NOTE		
1.	In plane	
2.	In plane	
3.	Perpendicular to plane	
4.	Perpendicular to plane	
5.	5 minute test	
6.	2 minute test	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
 Phone: +86 13424755533  
 Email: sales@su-jiao.com  
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT