

PRL PEI-G40

Polyether Imide
Polymer Resources Ltd.

Message:

PRL PEI-G40 is a Polyether Imide (PEI) product filled with 40% glass fiber. It can be processed by injection molding and is available in North America. Characteristics include:
Flame Rated
RoHS Compliant
Flame Retardant
Heat Resistant

General Information			
UL YellowCard	E113219-219252		
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
	High Heat Resistance		
RoHS Compliance	RoHS Compliant		
UL File Number	E113219		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.60	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (337°C/6.6 kg)	3.0 to 18	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.10 to 0.30	%	ASTM D955
Water Absorption			ASTM D570
24 hr	0.13	%	
Equilibrium, 23°C	0.90	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	114		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (3.18 mm)	11700	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield, 3.18 mm	177	MPa	
Break, 3.18 mm	177	MPa	
Tensile Elongation (Break, 3.18 mm)	2.5	%	ASTM D638
Flexural Modulus (3.18 mm)	11700	MPa	ASTM D790
Flexural Strength (3.18 mm)	234	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	96	J/m	ASTM D256
Unnotched Izod Impact (23°C, 3.18 mm)	430	J/m	ASTM D4812

Reverse Notch Izod Impact (23°C, 3.18 mm)	480	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	214	°C	
1.8 MPa, Unannealed, 3.18 mm	212	°C	
Vicat Softening Temperature	232	°C	ASTM D1525 ¹
CLTE - Flow (-20 to 150°C)	1.4E-5	cm/cm/°C	ASTM E831
RTI Elec			UL 746
1.50 mm	105	°C	
3.00 mm	105	°C	
RTI Imp			UL 746
1.50 mm	105	°C	
3.00 mm	105	°C	
RTI Str			UL 746
1.50 mm	105	°C	
3.00 mm	105	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.5E+16	ohms·cm	ASTM D257
Dielectric Strength (1.59 mm, in Oil)	24	kV/mm	ASTM D149
Dielectric Constant (1 kHz)	3.70		ASTM D150
Dissipation Factor (1 kHz)	2.0E-3		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	V-0		
3.00 mm	V-0		
Injection	Nominal Value	Unit	
Drying Temperature	143 to 149	°C	
Drying Time	4.0 to 6.0	hr	
Drying Time, Maximum	8.0	hr	
Rear Temperature	332 to 399	°C	
Middle Temperature	338 to 399	°C	
Front Temperature	343 to 399	°C	
Processing (Melt) Temp	338 to 399	°C	
Mold Temperature	107 to 177	°C	
NOTE			
1.	Rate B (120°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

