

EVICOM™ RC7/025

Rigid Polyvinyl Chloride

INEOS Compounds

Message:

The values listed for Tensile Modulus were tested at an unspecified rating.

The values listed for Coefficient of Thermal Expansion were tested at an unspecified rating.

The values listed for Thermal Conductivity were tested at an unspecified rating.

General Information			
Features	Impact resistance, good		
	Compliance of Food Exposure		
Appearance	Clear/transparent		
Forms	Particle		
Processing Method	Blow molding		
Hardness	Nominal Value	Test Method	
Rockwell Hardness (R-Scale)	115	ASTM D785	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2.80	MPa	ASTM D638
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow	6.0E-5	cm/cm/°C	ASTM D696
Thermal Conductivity	0.16	W/m/K	ASTM C177
Additional Information			

Vicat Softening Point, BS2782 120B: 63°CVCMM Content, EEC Directive 81/432/CEE: < 1.0 PPM

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT