

ISPLEN® PP 030 G1E

Polypropylene Homopolymer
REPSOL

Message:

ISPLEN® PP 030 G1E is a medium-low melt flow rate polypropylene homopolymer. It offers an optimum balance between mechanical and processing properties for production of monofilaments and tapes with high tensile strength at break. It is formulated with an additive package suitable for protecting the polymer during extrusion process and final use.

TYPICAL APPLICATIONS

- High tenacity monofilaments and tapes for ropes and twines
- Tapes for textil uses
- Extruded nets
- Strap
- Sheet extrusion
- Blow molding
- Recommended melt temperature range from 190 to 250°C. Processing conditions should be optimised for each production line.

General Information			
Additive	Processing Stabilizer		
Features	Food Contact Acceptable		
	High Tensile Strength		
	Medium Flow		
Uses	Blow Molding Applications		
	Monofilaments		
	Netting		
	Rope		
	Sheet		
	Strapping		
	Tape		
	Twine		
Agency Ratings	EU Food Contact, Unspecified Rating		
Processing Method	Blow Molding		
	Extrusion		
	Filament Extrusion		
	Sheet Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.905	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	1.7	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	34.0	MPa	ISO 527-2
Flexural Modulus	1250	MPa	ISO 178

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	90.0	°C	ISO 75-2/B
Vicat Softening Temperature	152	°C	ISO 306/A
Extrusion	Nominal Value	Unit	
Melt Temperature	190 to 250	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

