# Vipel® F737-FBG-36

# Polyester Alloy

AOC, L.L.C.

## Message:

AOC's Vipel F737 Series is a resilient isophthalic polyester resin with excellent mechanical properties. Vipel F737 resins are used extensively in grating and in the construction of large diameter water pipes for transporting water to and from power stations. Vipel F737 Series resins can be adapted for a variety of fabrication processes.

#### BENEFITS

#### Internationally Recognized

Vipel F737 series resins have been used in many corrosion resistant applications such as grating and water pipes, etc.

Corrosion Resistance

This resin provides excellent corrosion resistance when used in contact with inorganic and organic acids. Refer to AOC's "Corrosion Resistant Resin Guide" for corrosion resistance information or for questions regarding suitability of a resin to any particular chemical environment contact AOC.

Versatile

Suitable for various fabricating methods such as hand lay-up, spray-up, filament winding, etc.

General Information					
Features	m-benzene dimethyl				
	Good corrosion resistance				
	acid resistance				
	Elastic				
Uses	Piping system				
Agency Ratings	FDA 21 CFR 177.2420				
Forms	Liquid				
Processing Method	Filament power winding				
	Sprayable				
	Hand coating				
Physical	Nominal Value	Unit	Test Method		
Styrene Content	44	%			
Gel to Peak	6.0	min			
Peak Exotherm	185	°C			
Thixotropic Index <sup>1</sup>	2.50				
Hardness	Nominal Value	Unit	Test Method		
Barcol Hardness	39		ASTM D2583		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Modulus	3380	MPa	ASTM D638		
Tensile Strength	85.5	MPa	ASTM D638		
Tensile Elongation (Break)	4.0	%	ASTM D638		
Flexural Modulus	3930	MPa	ASTM D790		
Flexural Strength	141	MPa	ASTM D790		
Impact	Nominal Value	Unit	Test Method		

Notched Izod Impact	220	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1	.8		
MPa, Unannealed)	91.7	°C	ASTM D648
Uncured Properties	Nominal Value	Unit	
Density	1.08	g/cm³	
Viscosity (25°C, Brookfield LV)	0.55	Pa·s	
Gel Time (25°C)	36	min	
NOTE			
1.	6/60 rpm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

