

Latimass 62-07 D025

Polyamide 6

LATI S.p.A.

Message:

Specific density compound based on Polyamide 6 (PA6).

Special filler.

General Information			
Filler / Reinforcement	Filler		
Physical	Nominal Value	Unit	Test Method
Density	2.56	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 294-4
Across Flow : 2.00 mm	0.40 to 0.60	%	
Flow : 2.00 mm	0.35 to 0.55	%	
Water Absorption (23°C, 24 hr)	0.22	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	11500	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	80.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	1.5	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	25	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	215	°C	ISO 75-2/B
1.8 MPa, Unannealed	190	°C	ISO 75-2/A
Continuous Use Temperature ²	90.0	°C	
Vicat Softening Temperature	195	°C	ISO 306/B50
CLTE - Flow (30 to 100°C)	8.0E-6	cm/cm/°C	ISO 11359-2
Thermal Conductivity	1.7	W/m/K	Internal Method
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 100	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	250 to 290	°C	
Mold Temperature	80.0 to 100	°C	
Injection Rate	Moderate		
NOTE			
1.	60 MPa		
2.	20,000 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

