

# Huaфон T26P

Polyamide 66  
Huaфон Group Co., Ltd.

Message:

T26P is light middle viscosity of co-polymerization.  
Typical Applications  
T26P can be used for spinning fine denier staple fibre, mainly for the production of high-grade cashmere imitation, wool fabrics and other staple fibre products.

General Information			
Features	Medium Viscosity		
Uses	Fabrics		
	Staple Fibers		
Processing Method	Fiber (Spinning) Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm <sup>3</sup>	ISO 1183
Apparent Density	0.70	g/cm <sup>3</sup>	Internal Method
Particle Size	1.70 to 2.30	g/100 pellets	Internal Method
Relative Viscosity			Internal Method
Dry Chips	2.62 to 2.70		
Wet Chips	2.58 to 2.66		
Water Content			Internal Method
Dry Chips	< 800	mg/kg	
Wet Chips	< 5000	mg/kg	
Thermal	Nominal Value	Unit	Test Method
Peak Melting Temperature <sup>1</sup>	260	°C	ASTM D3418
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT