## Karina MB CONC DE PIGMT RED -E 42/234-FC-LMP

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

## Message:

PIGMENT CONCENTRATE RECOMMENDED FOR EXTRUSION GENERAL PVC - MINIMUM USAGE 2% - ORGANIC AND INORGANIC.

General Information			
Uses	Color Concentrates		
Appearance	Red		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density <sup>1</sup>	1.27 to 1.33	g/cm³	IEC 60811-1-3
Color	OK		ME 12
Color a	40.3 to 43.3		ME 12
Color b	19.9 to 22.9		ME 12
Color L	38.2 to 41.2		ME 12
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	70 to 74		NBR 7456
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity <sup>2</sup>	> 1.0E+14	ohms·cm	NBR 5403
NOTE			
1.	24 hr		
2.	24 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

