

Tarnamid® T- 27 Z1

Polyamide 6
Grupa Azoty S.A.

Message:
Impact modified.

General Information				
Additive		Impact Modifier		
Features		Impact Modified		
Uses		Appliances		
		Automotive Applications		
		Electrical/Electronic Applications		
		Household Goods		
Appearance		Black		
		Colors Available		
		Natural Color		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.11	--	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (275°C/5.0 kg)	110	--	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (2.00 mm)	0.70	--	%	ISO 294-4
Water Absorption				ISO 62
Saturation, 23°C	9.5	--	%	
Equilibrium, 23°C, 50% RH	2.8	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness (H 358/30)	150	--	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	2800	--	MPa	ISO 527-2/1
Tensile Stress (Yield)	72.0	--	MPa	ISO 527-2/50
Tensile Strain (Break)	40	--	%	ISO 527-2/50
Flexural Modulus ¹	2200	--	MPa	ISO 178
Flexural Stress ²	75.0	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	10	--	kJ/m ²	ISO 179/1eA

Notched Izod Impact Strength	10	--	kJ/m ²	ISO 180
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	55.0	--	°C	ISO 75-2/A
Vicat Softening Temperature	195	--	°C	ISO 306/B
Melting Temperature	221	--	°C	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+16	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+16	1.0E+13	ohms·cm	IEC 60093
Electric Strength (2.00 mm)	21	19	kV/mm	IEC 60243-1
Dielectric Constant (1 Hz)	3.40	3.50		IEC 60250
Dissipation Factor (1 Hz)	0.020	0.10		IEC 60250
Comparative Tracking Index (Solution A)	600	600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (3.20 mm)	HB	--		UL 94
Additional Information	Dry	Conditioned		Test Method
ISO Type	PA6-HI, MR, 14020	--		ISO 1874
Injection	Dry	Unit		
Drying Temperature	< 80.0		°C	
Suggested Max Moisture	< 0.10		%	
Suggested Max Regrind	50		%	
Processing (Melt) Temp	240 to 260		°C	
Mold Temperature	40.0 to 60.0		°C	
Injection Pressure	80.0 to 110		MPa	
Injection Rate	Moderate			
NOTE				
1.	2.0 mm/min			
2.	2.0 mm/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT